



i n t e r w a r e

MM - 80[®]

**CHEMICAL
RESISTANCE**

Chemical Resistance Ratings for MM-80[®] Semi-Rigid Epoxy

CHEMICAL	RATING	COMMENTS
Acetic Acid 0-20%	A	
Acetic Acid 20-30%	C	Remove within 30 minutes
Alkaline Cleaners	A	
Antifreeze	A	
Battery Acid	C	Remove within 30 minutes
Corn Oil	A	
Dextrose	A	
Ethylalcohol	C	May temporarily soften MM-80 [®]
Gasoline	A	
Grape Juice	A	
Hydraulic Fluid	A	
Hydrochloric Acid	NR	Remove promptly
Isopropyl Alcohol	A	May temporarily soften MM-80 [®]
Jet Fuel	A	
Lactic Acid 20%	A	
Methyl Ethyl Ketone	C	May temporarily soften MM-80 [®]
Milk	A	
Molasses	A	
Motor Oil	A	
Muriatic Acid 5%	A	
Salicylic Acid	A	
Salt Brine	A	
Sky Drol (phosphate ester hydraulic fluid)	A	
Sky Drol 500 B-4	A	
Strong Detergents	A	
Sugar	A	
Toluol (toluene)	C	May temporarily soften MM-80 [®]
Wine	A	

TESTING STANDARD: ASTM-D 3912, 77°F (25°C)

Code Key:

A – Acceptable

C – Conditional

NR – Not Recommended

INTERWARE Comercial e Serviços Ltda.

Av. Brig^o Faria Lima, 1.685 – cj 2C – Jd. Paulistano

01452-916 – São Paulo – SP

Fone: 55 11 3815-0953

e-mail: vendas@interware.com.br